



義大利進口磁磚

一澤家居・澤 Living









AX-2012-BE-N
20x120 cm.





AX-2012-BE-N
20x120 cm.





AX-2012-BE-N
20x120 cm.



AXEL

20x120










AX-2012-GR-N
20x120 cm.

米色		淺棕色		灰色	
----	--	-----	--	----	--



AX-2012BE-N.
\$500元/片



AX-2012GO-N.
\$500元/片



AX-2012GR-N.
\$500元/片

厚度	色差 V3	DIN 51130	耐磨性
▼ 10.3mm ▲			≥ 0,42

FORMATO	SPESSORE	Pzx	Mqx	Kgx	x	Mqx	Kgx
20x120	10.3	4	0.96	23,12	48	46.08	1110.00

CARATTERISTICHE TECNICHE
TECHNICAL STANDARDS
CHARACTERISTIQUES TECHNIQUES
TECHNISCHE EINGESCHAFTEN

		檢驗標準	標準值	AXEL
ASSORBIMENTO D'ACQUA WATER ABSORPTION WASSERAUFNAHME ABSORPTION D'EAU ABSORCIÓN DE AGUA		UNI EN ISO 10545-3	$\leq 0,5\%$	$\leq 0,1\%$
RESISTENZA ALLA FLESSIONE BENDING STRENGTH BIEGEFESTIGKEIT RÉSISTANCE À LA FLEXION RESISTENCIA A LA FLEXIÓN		UNI EN ISO 10545-4	$\geq 35 \text{ N/mm}^2$	$\geq 45 \text{ N/mm}^2$
RESISTENZA CHIMICA CHEMICAL RESISTANCE CHEMIKALIENBESTÄNDIGKEIT RÉSISTANCE CHIMIQUE RESISTENCIA QUÍMICA		UNI EN ISO 10545-13	Resistenza a sali da piscina o additivi ad uso domestico – Classe GB minimo Resistance to swimming pool salts or additives for domestic use – class GB minimum. Résistance au sel de piscine ou additif domestique – classe GB minimum. Resistent gegen Salze in Schwimmbäder sowie im Haushaltsgebrauch = Klasse Minimum GB.	RESISTE RESISTS RESISTE STANDHALTET
			Resistenza ad acidi e basi a bassa concentrazione – Dichiarato dal fabbricante Resistance to acid and bases with low concentration – declared by the manufacturer. Résistance aux acides et bases à basses concentration – Déclaration du fabricant. Niedrig konzentrierte Säure und Basen beständigkeit, Herstellererklärung.	-
			Resistenza ad acidi e basi ad alta concentrazione – Metodo di prova disponibile Resistance to acids and bases with high concentration – test method available. Résistances aux acides et bases à hautes concentration – méthodes de preuve disponible. Hoch konzentrierte Säure und Basen beständigkeit, Prüfzeugnis Verfügbar.	-
DUREZZA SUPERFICIALE (SCALA MOHS) MOHS' HARDNESS RITZHÄRTE DER OBERFLÄCHE DURETÉ SUPERFICIELLE À LA RAYURE DUREZA SUPERFICIAL (ESCALA MOHS)		CTI - 81-7	-	≥ 5
RESISTENZA ALLE MACCHIE RESISTANT TO STAINING FLECKENBESTÄNDIGKEIT RÉSISTANCE AUX TACHES RESISTENCIA A LAS MANCHAS		UNI EN ISO 10545-14	≥ 3	≥ 4

Vista l'ampia gamma di prodotti i valori sopra riportati sono la media della gamma produttiva.

Because the selection of products is very wide, the figures given above are the average for the product range.

Etant donné la vaste gamme de produits les valeurs rapportées sont la moyenne de la gamme de production.

Angeichts des großen Produktangebots sind die oben wiedergegebenen Werte Durchschnittswerte, die sich auf die gesamte Produktion beziehen.

● **Conforme:** Complies with the standard - Conforme aux normes - Anforderungen erfüllt



Ceramics of Italy

 pastorelli

I.TSER
一澤家居 Living

一澤貿易有限公司

旗艦展示中心
新北市新北產業園區五權路 37 號
tel: 02-2298-1000

最新資訊
www.i-tser.com.tw

copyright © 一澤貿易有限公司 All Rights Reserved.